



PTFE



Špeciálne mazacie tuky s PTFE

Špeciálne mazacie tuky s PTFE

Mazací tuk	NGLI	NSF	Zahusťo- vadlo	Základový olej	Teplota °C	Tuhé mazivo
G.BESLUX FLUOR H	0.2.2/3,3	áno	PTFE	PFPE	-40 do 260	PTFE
G.BESLUX FLUOR L-2	2	nie	PTFE	PFPE	-50 do 160	PTFE
G.BESLUX BESSIL EH	000,00,3	áno	Anorg.	Silikon	-45 do 180	PTFE
G.BESLUX ELG-54	00	nie	Anorg.	Silikon	-45 do 180	PTFE
G.BESLUX BESSIL L-80/1 PLUS	1	nie	Lítium	Silikon	-50 do 150	PTFE
G.BESLUX BESSIL M-1/TF PLUS	1	nie	Lítium	Silikon	-50 do 250	PTFE
G.BESLUX BESSIL 120	2	nie	LiCx	Silikon	-50 do 160	PTFE
G.BESLUX PASTE TF--3	3	nie	Anorg.	Syntetic	-40 do 200	PTFE
G.BESLUX ATOX TF/S	2/3	áno	Anorg.	Syntetic.	-40 do 180	PTFE
G.BESLUX KOMPLEX M-2/1 STF	1/2	nie	Polymo- čovina	Syntetic.	-40 do 180	PTFE
G.BESLUX LIPLEX AG-1/2	1/2	nie	LiCx	Syntetic.	-40 do 180	PTFE
G.BESLUX LIPLEX L-2 STF PLUS	2	nie	LiCx	Syntetic.	-50 do 170	PTFE
G.BESLUX PLEX DPH 8113	2	nie	Lítium	Syntetic.	-55 do 150	PTFE
G.BESLUX PLEX 778A/TF	2	nie	Lítium	Syntetic.	-55 do 150	PTFE
G.BESLUX PLEX 778B/TF PLUS	2	nie	Lítium	Syntetic.	-55 do 150	PTFE
G.BESLUX MP EH-2/S	2	nie	Lítium	Syntetic.	-40 do 150	PTFE
G.BESLUX ELG-232	1/2	nie	Lítium	Syntetic.	-40 do 150	PTFE
G.BESLUX WHITE FOOD GREASE	2	áno	Anorg.	medicínsky biely	-15 do 120	PTFE
G.A.N.800 TF	2	nie	Lítium	Mineral	-30 do 120	PTFE
G.A 5A3	1	nie	Lítium	Minderal	-10 do 110	PTFE

PTFE (Polytetrafluoroetylen)
PFPE (Perfluoropolyetylen)

Zastúpenie na Slovensku:
SOLUTECH BOHEMIA SK, s.r.o
Stred 52
Považská Bystrica
01701
www.sbsk.sk